

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B62D 29/00	A1	(11) International Publication Number: WO 00/13958 (43) International Publication Date: 16 March 2000 (16.03.00)
(21) International Application Number: PCT/US99/18832 (22) International Filing Date: 2 September 1999 (02.09.99) (30) Priority Data: 09/149,978 9 September 1998 (09.09.98) US (71) Applicant: HENKEL CORPORATION [US/US]; Suite 200, 2500 Renaissance Boulevard, Gulph Mills, PA 19406 (US). (72) Inventor: WYCECH, Joseph, S.; 927 Lakeshore Road, Grosse Pointe Shores, MI 48236 (US). (74) Agent: HARPER, Stephen, D.; Henkel Corporation, Suite 200, 2500 Renaissance Boulevard, Gulph Mills, PA 19406 (US).	(81) Designated States: CA, IN, JP, KR, MX, TR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>	
<p>(54) Title: THREE DIMENSIONAL LAMINATE BEAM STRUCTURE</p> <div data-bbox="565 1134 925 1396"></div> <p>(57) Abstract</p> <p>A three-dimensional laminate beam (10) is formed by inserting a preformed foam core (18) insert within a hydra-formed metal section (12) having curved three-dimensional geometry. A reinforcing polymer (20) is pumped in and around the foam core insert so as to be adjacent the inside wall of the shell. The polymer bonds to the inside wall of the shell upon the polymer being cured.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

core insert so that after curing the polymer bonds to the inside wall of the structure.

In a preferred practice of the invention the structure is a hydra-formed metal section, such as a vehicle control arm assembly. The pre-shaped foam insert is preferably made of a lightweight material to minimize the weight of the final laminate beam formed by the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a perspective view of a laminated control arm assembly beam in accordance with this invention; and

Figure 2 is a cross-sectional view taken through Figure 1 along the line 2-2.

DETAILED DESCRIPTION OF THE INVENTION

The present invention is particularly useful for reinforcing hollow sections or structures, which are of curved geometry and/or located at locations, which are relatively inaccessible.

In the preferred practice of the invention the hollow structure is a metal section, such as a hydra-formed metal section with curved three-dimensional geometry. An example of such section is a control arm assembly, wherein it is desired to reinforce the control arm beam. For such hydra-formed section the critical portion which requires reinforcement in order to maximize the overall performance of the component is often the portion at a major section discontinuity "notch" or curvature. Figure 1, for example,

09/103.031 filed June 23, 1998, all of the details of that patent and application are incorporated herein by reference thereto.

The curing of the polymer could be accomplished in any suitable manner. For example, where the shell 12 is a vehicle component, the polymer could be heat cured in an oven such as an e-coat oven during the manufacturing of the vehicle. Alternatively, the polymer could be cured at ambient temperatures such as, for example, about 77°F.

The foam core insert 18 may be pre-shaped in a geometry which generally conforms to the inner surface of shell 12 thereby minimizing the amount of polymer material required to fill the remaining open space within shell 12. Alternatively, core insert 18 may be of uniform cross-sectional shape throughout all or most of its length to simplify the structure of the core insert, but which would result in a greater amount of open space. The foam core insert 18 thus comprises a three-dimensional or essentially two dimensional molded pre-formed part which occupies some of the volume or space within shell 12 and provides a substrate for the polymer 20 which is pumped into the shell 12.

The invention thus results in a three-dimensional laminate beam, which is formed by pumping the polymer around the pre-molded foam core. This is the only means necessary to reinforce such a hydra-formed metal section.

10. The beam of claim 3 wherein said polymer is ambient temperature curable.
11. A method of forming a three-dimensional laminate beam comprising the steps of inserting a pre-formed core insert within a hollow shell with the insert spaced from at least one inside wall of the shell and with the shell being of curved shape, pumping a reinforcing polymer in and around the core insert, and curing the polymer to cause the polymer to bond to the inside wall of the shell.
12. The method of claim 11 including pre-molding the core insert from a lightweight foam material.
13. The method of claim 12 wherein the shell is made of a hydra-formed metal section of non-uniform shape along its length.
14. The method of claim 12 wherein the resulting beam is a vehicle control arm assembly.
15. The method of claim 13 wherein the resulting beam is a vehicle component.
16. The method of claim 15 wherein the polymer is heat cured.
17. The method of claim 15 wherein the polymer expands upon curing.
18. The method of claim 15 wherein the polymer is cured at ambient temperatures.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US99/18832

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :B62D 29/00

US CL :Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : Please See Extra Sheet.

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONEElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
NONE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	US 5,806,919 A (DAVIES) 15 SEPTEMBER 1998 (15/09/98), SEE ENTIRE DOCUMENT, ESPECIALLY FIGURES 1-2.	1-10
X,P	US 5,866,052 A (MURAMATSU) 02 FEBRUARY 1999 (02/02/99), SEE ENTIRE DOCUMENT, ESPECIALLY FIGURE 6(C).	1-10
X	US 4,722,563 A (LOREN ET AL.) 02 FEBRUARY 1988 (02/02/88), SEE ENTIRE DOCUMENT, ESPECIALLY FIGURE 11.	1-3, 7-12, 14-18
X	US 5,575,526 A (WYCECH) 19 NOVEMBER 1996 (19/11/96), SEE ENTIRE DOCUMENT, ESPECIALLY FIGURE 11.	1, 11, 13

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

A	Special categories of cited documents: document defining the general state of the art which is not considered to be of particular relevance	*T*	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
B	earlier document published on or after the international filing date	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
L	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
O	document referring to an oral disclosure, use, exhibition or other means	*A*	document member of the same patent family
P	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

13 OCTOBER 1999

Date of mailing of the international search report

09 DEC 1999

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

LAURA A. CALLO

Telephone No. (703) 305-2163

Form PCT/ISA/210 (second sheet)(July 1992)*